
















Technical specifications

Corklinoleum®

Corklinoleum meets the requirements of EN 688

	Thickness	4.5 mm	
 	Classification	EN 685	
		Class	22
		Class	31
	Collection size	12	
	Roll width	EN 426 2.00 m	
	Roll length	EN 426 ≤ 32 m	
	Static charge	EN 1815 < 2 kV	
	Fire rating	EN 13501-1 D _{s1}	
	Impact sound reduction	EN ISO 717-2 14 dB	
	Thermal conductivity	EN 12524 0.10 W/m·K	
	Residual indentation	EN 433 ± 0.35 mm	
	Colour fastness	ISO 105-B02 Method 3: blue scale minimum 6.	
	Chemical resistance	EN 423 Resistant to diluted acids, oils, fats and to the conventional solvents such as alcohol, white spirit, etc. Not resistant to prolonged exposure to alkalis.	
	Flexibility	EN 435 ø 40 mm	
	Bacteriostatic properties	Marmoleum has bacteriostatic properties, which are confirmed by independent laboratories, even against the bacteria MRSA.	
	Life Cycle Assessment	LCA is the foundation for securing the lowest environmental impact.	

The above information is subject to modifications for the benefit of further improvements.